



Composition® is manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under ISO 9001 and ISO 14001 certified Quality and Environmental Management Systems. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

**Specification**

**Product name** Composition®  
**Description** 100% polyester needle punched, thermally bonded wallcovering

	Metric
Roll width	1.22 m x 25 m
Thickness	10 - 12 mm
Tolerance	(+/- 5 mm) (+/- 10 mm)
Weight	Typically 1680 gsm

**Physical description/  
properties**

Boiling point:	N/A
Melting point:	250°C
Vapour pressure:	N/A
Specific gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative vapour density:	N/A

**Acoustic performance**

Composition is specifically designed to reduce and control reverberated noise and echo in building interiors.

Noise Reduction Coefficient 0.40

Frequency (Hz)	125	250	500	1000	2000	4000	NRC
● 10 - 12mm Composition	0.05	0.10	0.25	0.55	0.80	0.95	0.40

**Service**

For further information about Composition or any other Autex Acoustics® product, please contact your account manager or visit our website.

**Care and maintenance**

Maintain in accordance with the Care and Maintenance Guide available for this product.



## Product specifications

### Composition

100% polyester fibre from polyethylene terephthalate (PET). Composition® contains a minimum of 60% recycled polyester fibre.

### Suitable applications

Pinboard and acoustic wallcovering. Accepts pins and staples.

### Fire ratings

Composition has been evaluated using the following test methods:

#### ISO 9705: 1993

Classification: Group 1-S

Smoke production rate:

<5.0m<sup>2</sup>/s

As required by NZBC C/VM2

#### AS ISO 9705 - 2003

Classification: Group 1

(SMOGR<sub>Arc</sub>): <100m<sup>2</sup>/s<sup>2</sup>

Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637:2015, as required by BCA Specification C1.10-4 FI 4894 and FAR 4055

#### BS EN 13501-1:2018

Classification: B-s1,d0

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011. EUI-21-000135-C

#### ASTM E84 - 14

Class A, FS-5 - SD:25

Report RJ3297

### Thermal performance

R0.22 (@15°C)

### VOC emissions

Autex Acoustics polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered a low VOC product. VOC concentration: 0.009 mg/m<sup>3</sup> (7 days)

### Water vapour sorption

ASTM C1104 / C1104M-13a

Test conditions: 49°C, 95%RH

Water vapour absorbed and adsorped after 4 days:

0.4% by weight

### Impact resistance

ISO 7892:1988

### Hard body impact

There is no surface damage or penetration to Composition when subjected to hard body impacts. When adhered to 10 mm plasterboard, the system can resist a 9 joule impact. This is equivalent to the impact of a 0.5 kg object dropped from a 2 m height. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5 kg object dropped from a 0.5 m height.

### Soft body impact

There is no surface damage or penetration to Composition when subjected to soft body impacts. When adhered to 10 mm plasterboard, the system can resist a 70 joule impact. This is equivalent to the impact of a 50 kg object dropped from a 150 mm height.

### Microbial resistance

ASTM G21-15

Growth rating: 0 (No growth)

Composition does not promote the growth of moulds and mildew.

### Colour fastness to light

Composition is suitable for indoor use only.

Light fastness is dependent on use and exposure.

Composition has been evaluated to the following standard:

ISO 105-B02:2014

Rating: 6 (Highest = 7)

### Colour fastness to rubbing

ISO 105-X12:2016

Dry rating: 4-5 (Highest = 5)

Wet rating: 4-5 (Highest = 5)

### Moisture absorption

Polyester fibre when exposed to an atmosphere of 50°C at 90% relative humidity for four days showed moisture absorption of less than 0.03% by weight. Polyester is not affected by moisture and will not rot or deteriorate in intended use situations.

### Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution.

Custom printed Composition requires the services of a specialist cleaning company. Refer to the Composition Care and Maintenance Guide for more information.

### Finish

Non-woven. No pattern repeat but Composition has a directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

## Environmental

Autex Acoustics is committed to best practice through our ISO 14001 certified Environmental Management Systems.

Composition contains a minimum of 60% previously recycled polyester fibre (from PET bottle-flake). Off-cuts and manufacturing waste are re-used or recycled wherever possible.

Composition is manufactured from 100% polyester fibre and does not contain formaldehyde binders. Autex Acoustics polyester fibre supports safer indoor air quality and will not become a potential airborne pollutant.

#### ● Autex Industries Ltd

702-718 Rosebank Rd  
Private Bag 19988  
Avondale 1746, Auckland  
New Zealand  
Freephone 0800 428 839  
Phone +64 9 828 9179  
Fax +64 9 828 5810

#### ● Autex Australia Pty Ltd

166 Bamfield Road  
PO Box 5099  
West Heidelberg, Melbourne  
VIC 3081, Australia  
Freephone 1800 678 160  
Phone +61 3 9457 6700  
Fax +61 3 9457 1020

#### ● Autex Acoustics Ltd

Unit J4, Lowfields Way,  
Lowfields Business Park,  
Elland, West Yorkshire  
Hx5 9Da  
United Kingdom  
Phone +44 0 1422418899

#### ● Autex Acoustics LLC

19350 Van Ness Avenue  
Torrance, CA 90501  
United States of America  
Phone +1 424 203 1813