



# INTERIOR ACOUSTICS

# HORIZON™

## MANUFACTURER'S GUARANTEE

Horizon™ panels are manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under ISO 9001 and ISO 14001 certified Environmental and Quality Management Systems. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

<b>Product Name</b>	Horizon
<b>Description</b>	100% polyester lightweight semi-rigid panel.
<b>Panel Dimensions</b>	Available in 6 geometric shapes. Please refer to Horizon brochure for individual dimensions

### COMPOSITION

100% polyester fibre from polyethylene terephthalate (PET). Horizon contains a minimum of 60% previously recycled polyester fibre.

### SUITABLE APPLICATIONS

Suspended or wall mounted acoustic panels.

### BOX CONTENTS

Please refer to brochure.

### COLOUR FASTNESS TO LIGHT

Horizon is suitable for indoor use only. Light fastness is dependent on use and exposure. Horizon has been evaluated to the following standard:

ISO 105-B02:2014

Rating: 6 (Highest = 7)

### ACOUSTIC PERFORMANCE

Horizon is specifically designed to reduce and control reverberation and echo noise in building interiors. For a copy of the full acoustic report please contact your Autex account manager.

### VOC EMISSIONS

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered a low VOC product.

VOC concentration: 0.009 mg/m<sup>3</sup> (7 days)

### FIRE RATINGS

Horizon is made from Cube™ as the base material. Cube (24mm) has been evaluated using the following test methods:

#### ISO 9705: 1993

Classification: Group 1-S

Smoke Production Rate: <5.0m<sup>2</sup>/s

As required by NZBC C/VM2

#### AS ISO 9705 - 2003

Australian Group Number: Group 1

SMOGRARC: less than 100m<sup>2</sup>/s<sup>2</sup>

Assessed using methodology AS ISO 9705:2003

in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4.

FAR 4055

#### ASTM E-84-15a

Class A, FS:0 - SD:65

RJ4479

### FINISH

Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

### PHYSICAL DESCRIPTION/PROPERTIES

Boiling point:	N/A
Melting point:	250°C   482°F
Vapour pressure:	N/A
Specific gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative vapour density:	N/A

### CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.



www.autexglobal.com

AN ISO 9001 AND ISO 14001 CERTIFIED COMPANY

#### Autex Industries Ltd

702-718 Rosebank Rd,  
Private Bag 19988,  
Avondale 1746, Auckland,  
New Zealand  
Freephone **0800 428 839**  
Phone **+64 9 828 9179**  
Fax **+64 9 828 5810**

#### Autex Australia Pty Ltd

166 Bamfield Road,  
PO Box 5099,  
West Heidelberg, Melbourne,  
VIC 3081, Australia  
Freephone **1800 679 160**  
Phone **+61 3 9457 6700**  
Fax **+61 3 9457 1020**

#### Autex Acoustics Ltd

Unit 14, Lowfields Way,  
Lowfields Business Park,  
Elland, West Yorkshire,  
HX5 9Da,  
United Kingdom  
Phone **+44 0 1422 418899**

#### Autex Acoustics LLC

19350 Van Ness Avenue  
Torrance, CA 90501  
United States of America  
Phone **+1 424 203 1813**

The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2020 Autex Industries Ltd. All Rights Reserved.

It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.

