



# INTERIOR ACOUSTICS

# ACCENT CEILING TILE™

## MANUFACTURER'S GUARANTEE

Accent Ceiling Tile™ are manufactured by Autex Industries Ltd under ISO 14001 certified Quality Management system. This product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all the performance properties stated within this guarantee.

**Product Name** Accent Ceiling Tile

**Description** 100% polyester needle punched, thermally bonded ceiling tile with impervious layer.

AUTEX	
Size	595mm x 1195mm
Thickness	13mm
Tolerance	(+/- 6%)
Weight	3100gsm
Density	239kg/m <sup>3</sup>

### COMPOSITION

100% polyester fibre from polyethylene terephthalate (PET). Accent Ceiling Tile contains a minimum of 60% recycled polyester fibre.

### SUITABLE APPLICATIONS

High performing acoustic ceiling tile for reverberation control in commercial and education environments.

### FIRE RATINGS

ISO 9705: 1993

Classification: Group 1-S

Smoke Production Rate: <5.0m<sup>2</sup>/s

As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGRARC): <100m<sup>2</sup>/s<sup>2</sup>

Assessed using methodology AS ISO 9705 - 2003

in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4

FAR 4055

EN13501-1:2007+A1: 2009

B - s2, d2

Report WF 336911

### VOC EMISSIONS

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered a low VOC product.

VOC concentration: 0.009 mg/m<sup>3</sup> (7 days)

### BACK LOADING

None. All loads to be independently supported or transferred to the grid. For questions and concerns please contact your Autex account manager.

### ACOUSTIC PERFORMANCE

Accent Ceiling Tile is specifically designed to reduce and control reverberated (echo) noise in building interiors.

Minimum Noise Reduction Coefficient 0.85

Acoustic testing to ISO 354. University of Auckland Testing Service Tested with 300mm | 11.81" airgap. Accent Ceiling Tiles - Test No. T1632-2

	University of Auckland Test report Number	125	250	500	1000	2000	4000	NRC
Accent Ceiling Tile with 300mm airgap	T1632-2	0.70	0.80	0.80	0.90	1.00	1.00	<b>0.85</b>

### PHYSICAL DESCRIPTION/PROPERTIES

Boiling point:	N/A
Melting point:	250°C   482°F
Vapour pressure:	N/A
Specific gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative vapour density:	N/A

### CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.

**AUTEX**  
Interior Acoustics

www.autexglobal.com

AN ISO 9001 AND ISO 14001 CERTIFIED COMPANY

**Autex Industries Ltd**  
702-718 Rosebank Rd,  
Private Bag 19988,  
Avondale 1746, Auckland,  
New Zealand  
Freephone 0800 428 839  
Phone +64 9 828 9179  
Fax +64 9 828 5810

**Autex Australia Pty Ltd**  
166 Bamfield Road,  
PO Box 5099,  
West Heidelberg, Melbourne,  
VIC 3081, Australia  
Freephone 1800 678 160  
Phone +61 3 9457 6700  
Fax +61 3 9457 1020

**Autex Acoustics Ltd**  
Unit J4, Lowfields Way,  
Lowfields Business Park,  
Elland, West Yorkshire,  
HX3 9DA,  
United Kingdom  
Phone +44 0 1422 418899

**Autex Acoustics LLC**  
19350 Van Ness Avenue  
Torrance, CA 90501  
United States of America  
Phone +1 424 203 1813

The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2020 Autex Industries Ltd. All Rights Reserved.  
It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.

