



INTERIOR ACOUSTICS

HORIZON™

MANUFACTURERS GUARANTEE

Horizon™ panels are manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under an ISO 9001 certified Quality Management System. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

Product Name	Horizon	EN13501-1:2007+A1:2009
Description	100% polyester lightweight semi-rigid panel.	B - s2, d2 WF336911 dated 25th February 2014
Panel Dimensions	Available in 5 geometric shapes. Please refer to Horizon brochure for individual dimensions.	ASTM E-84-15a Class A, FS:0 - SD:65 RJ4479-1 dated 25th January, 2016

COMPOSITION

100% Polyester Fiber from polyethylene terephthalate (PET). Horizon contains a minimum of 45% previously recycled polyester fiber.

SUITABLE APPLICATIONS

Suspended or wall mounted acoustic panels.

BOX CONTENTS

Please refer to brochure.

COLOR FASTNESS TO LIGHT

Horizon is suitable for indoor use only. Light fastness is dependent on use and exposure. Horizon has been evaluated to the following standard:

ISO 105-B02:2014
Rating: 6 (Highest = 7)

FIRE RATINGS

Horizon™ is a value-added product made from Autex Cube™ acoustic panels as the base material. Cube™ (24mm) has been evaluated using the following test methods:

ISO 9705: 1993
Classification: Group 1-S
Smoke Production Rate: <5.0m2/s
As required by NZBC C/VM2

AS ISO 9705 - 2003
Australian Group Number: Group 1

SMOGRARC: less than 100m2/s2
Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4.
FAR 4055-2 dated 8th October, 2013

ACOUSTIC PERFORMANCE

Horizon is specifically designed to reduce and control reverberated (echo) noise in building interiors. For a copy of the full acoustic report please contact your Autex Account Manager.

VOC EMISSIONS

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered as a low VOC product.
VOC concentration: 0.009 mg/m³ (7 days)

FINISH

Product may vary from samples and batch to batch due to fiber blending and lay-up which is an inherent feature of this product.

PHYSICAL DESCRIPTION / PROPERTIES

Boiling point:	N/A
Melting point:	250°C 482°F
Vapor pressure:	N/A
Specific gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative vapor density:	N/A

CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.