



INTERIOR ACOUSTICS

QUIETSPACE® PANEL

MANUFACTURER'S GUARANTEE

Quietspace® Panel is manufactured by Autex Industries Ltd under an ISO 9001 and ISO 14001 certified Environmental and Quality Management System. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

Product Name Quietspace® Panel
Description 100% polyester fibre needle punched and thermally bonded

AUTEX	METRIC				IMPERIAL			
Panel Dimensions	1220mm x 2440mm				4' x 8'			
	(+5mm/-0mm) x (+10mm/-0mm)				(+0.20") x (+0.39")			
Thickness	25mm	50mm	75mm	100mm	1"	2"	3"	4"
Tolerance	(+/- 6%)				(+/- 6%)			
Weight	2300gsm	3800gsm	4050gsm	4300gsm	7.54oz/ft ²	12.45oz/ft ²	13.27oz/ft ²	14.09oz/ft ²

COMPOSITION

100% polyester fibre from polyethylene terephthalate (PET). Quietspace Panel contains a minimum of 45% recycled polyester fibre.

SUITABLE APPLICATIONS

High-performance acoustic control for building interiors including: theatres, auditoriums, recording/broadcasting studios, gymnasiums, open-plan offices, restaurants, and classrooms.

LIGHT REFLECTANCE

Nude White Quietspace Panel is suitable for indoor use only and has a light reflectance value of 83 (measured in accordance with BS 8493:2008+A1:2010).

FIRE RATINGS

(Testing results for 25mm & 50mm Quietspace® Panel)

ISO 9705: 1993

Classification: Group 1-S
Smoke Production Rate: <5.0m²/s
As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1
(SMOGRARC): <100m²/s2
Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4.
FI 4871
FAR 4055

EN13501-1:2007 (25mm Quietspace® Panel)

B - s2, d0
Report 185157

EN13501-1:2007+A1:2009 (50mm Quietspace® Panel)

B - s2, d2
Report WF 336912

ASTM E-84-14: (1" Quietspace® Panel)

Class A FS:0 - SD:10
Report RJ3297

ACOUSTIC PERFORMANCE

Quietspace Panel is specifically designed to reduce and control reverberation and echo noise in building interiors.

Minimum Noise Reduction Coefficient 0.85

Acoustic testing to ISO 354. University of Auckland Testing Service Report

	University of Auckland Test report Number	Frequency (Hz)						NRC
		125	250	500	1000	2000	4000	
25mm	T0712-18	0.15	0.45	0.85	1.00	1.00	1.00	0.85
50mm	T1228-8	0.30	0.75	1.00	1.00	1.00	1.00	1.00
75mm	T1905-4	0.50	0.90	1.00	1.00	1.00	0.95	1.00
100mm	T1905-5	0.65	1.00	1.00	1.00	0.95	0.95	1.00

IMPACT RESISTANCE

ISO 7892:1988

Hard Body Impact

There is no surface damage or penetration to Quietspace panel when subjected to hard body impacts. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5kg object dropped from a 0.5m height. When adhered to 10mm plasterboard, the system can resist a 14-joule impact, and no further indentations are observed. This is equivalent to the impact of a 0.5kg object dropped from a 3m height.

Soft Body Impact

There is no surface damage or penetration to Quietspace Panel when subjected to soft body impacts. When adhered to 10mm plasterboard, the system can resist a 120-joule impact. This is equivalent to the impact of a 50-kg object dropped from a 250mm height.

THERMAL PERFORMANCE

(Internally tested by Autex Lab)

25mm: R0.6 (@15°C)
50mm: R1.4 (@15°C)
75mm: R1.9 (@15°C)
100mm: R2.4 (@15°C)

VOC EMISSIONS

Autex polyester has been tested by Cetec Pty Ltd (Report: CV170908) for chemical emission and is classified as low VOC.

VOC concentration: 0.009 mg/m³ (7 days)



PHYSICAL DESCRIPTION / PROPERTIES

Boiling Point:	N/A
Melting Point:	250°C 482°F
Vapour Pressure:	N/A
Specific Gravity:	Polyester 1.38
Flash Point:	N/A
Explosive Limits:	N/A
Solubility In Water:	Not soluble
Alkalinity:	pH 7.8
Relative Vapour Density:	N/A

CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.



www.autexglobal.com

AN ISO 9001 AND ISO 14001 CERTIFIED COMPANY

Autex Industries Ltd
702-718 Rosebank Rd,
Private Bag 19988,
Avondale 1746, Auckland,
New Zealand
Freephone **0800 428 839**
Phone **+64 9 828 9179**
Fax **+64 9 828 5810**

Autex Australia Pty Ltd
166 Bamfield Road,
PO Box 5099,
West Heidelberg, Melbourne,
VIC 3081, Australia
Freephone **1800 678 160**
Phone **+61 3 9457 6700**
Fax **+61 3 9457 1020**

Autex Acoustics Ltd
Unit J4, Lowfields Way,
Lowfields Business Park,
Elland, West Yorkshire,
HKS 9Da,
United Kingdom
Phone **+44 0 1422 418899**

Autex Acoustics LLC
19350 Van Ness Avenue
Torrance, CA 90501
United States of America
Phone **+1 424 203 1813**

The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2020 Autex Industries Ltd. All Rights Reserved.

It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.